

Dehesa Mari Martí 28600 Navalcarnero (Madrid) Spain Tel +34 916 421 789 - Fax +34 916 421 834 general@afford-inks.com - www.afford-inks.com

98 SERIES GlassCure

Product Statement and Key Features:

The 98 Series range of UV Inks have been formulated to meet the needs of the industrial market for printing on glass, ceramics, metals and chrome plated surfaces.

98 Series is a multi cure ink system and formulated to cure with UV LED and traditional UV mercury vapour curing systems.

The ink is a 2 component system.

- Fast Curing
- Low Odour
- Unlimited Screen Stability
- Negligible Atmospheric Pollution
- Excellent physical and chemical resistance properties
- Resistant to acid, alkali, solvents, greases and lubricants, cosmetics, household products and detergents

Scope of Use:

98 Series inks from AFFORD are primarily designed for indoor decoration and promotional printed items of glass and ceramics, pre-treated flat glass for interior decoration use, interior doors, mirrors and glass for furniture use for example. Pre-treated cosmetic bottles, ceramics and metals are also suitable surfaces to print with AFFORD 98 Series.

Printing and Curing Guidelines:

These guidelines are intended only as a starting point for determining cure parameters, which must be determined under actual production conditions.

"Undercuring" the ink may result in poor adhesion, lower scuff resistance, reduced durability, and higher residual odour.

"Overcuring" the ink may reduce the flexibility of ink surface and the printed part and adhesion of subsequent ink layers.

Mercury Vapour UV Curing:

98 Series inks cure when exposed to a single medium pressure mercury vapour lamp meeting the following criteria:

120+ mJ/cm² @ 600+ mW/cm²

Mesh selection is critical for optimum results, meshes in the range 140T - 165T are recommended, image type and fabric will dictate the most appropriate mesh grade, please consult with AFFORD technical services for further guidance.





Inks can be affected by stray UV light. Be aware of skylights, windows and overhead lights curing the ink in the screen; light filters are recommended.

Leaving a container uncovered may result in the ink's surface forming a "skin", caused by reaction with ambient lighting. Keep containers covered.

Most stencil types are suitable, 11.170 (photopolymer) or 11.701 (diazo) are recommended. It is essential that the printed ink film is given time to fully cure to ensure full chemical and mechanical resistance is achieved and it is the user's responsibility to confirm the cure schedule by testing resistance properties and suitability prior to commencing a full production run.

Post Curing:

The chemical reaction initiated by UV radiation will continue for some time after initial exposure and the dried prints emerge from the dryer.

It is therefore important that the adhesion of the first colour down, and all subsequent overprint colours, is assessed at regular intervals.

Pre-treatment:

To achieve optimum adhesion to glass and ceramic surfaces and for optimal product resistance, consistent levels of surface cleansing/pre-treatment must be achieved.

A surface free energy of 46-52 dynes/cm is recommended and is best achieved with the use of a gas/air flame and the use of proprietary primers, for example Pyrosil™

IMPORTANT:

Stir inks well before every use.

Always test application fully before beginning any production run as supposedly similar surfaces can vary between different manufacturers, and even between different batches.

Product Resistance:

98 Series UV inks have generally better chemical and solvent resistance properties when compared to conventional inks and will resist attack by a wide range of products. Water resistance is excellent.

Resistance of prints immediately after cure is excellent, but for best results it is advisable to allow six hours after curing to achieve optimum resistance.

98 Series inks are not recommended for use in applications where outdoor exposure is a possibility.







Thinning and Wash Up:

98 Series inks are supplied ready for use; however, inks can be adjusted to suit print shop conditions and print speeds if necessary with the addition of 1-10% by weight of 80.008; in case of white inks, 80.005 is the recommended thinner.

Washing up of screens should be carried out using 52.001 Screen Cleaner.

Performance Improvement Additives and Mixing Instructions:

29.140 hardener will enhance adhesion and chemical resistance after 24 hours from printing. 80.007 is a thinner which will increase the flexibility of the film. Don't use more than 5%. 80.013 will enhance the thixotropic behaviour of the ink. A maximum of 5% should be added.

** All % additions are by weight **

Storage:

98 Series inks and additives should be stored at temperatures between 10-25°C with a relative humidity between 30 to 70%.

Safety Information Handling Instructions & Shelf Life:

Users are advised to wear gloves and barrier cream to prevent direct skin contact.

Safety glasses are suggested in areas where ink may be splashed. If ink does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvents or UV reducers).

Wash the affected area with soap and water.

Consult the applicable Safety Data Sheet (SDS) for further instructions and warnings.

This ink series is a one-part, 100% solids UV-curable screen-printing ink and does not contain N-vinyl-2-pyrrolidone (NVP).

Ink and cleaning solutions should always be kept away from heat, sparks, and flames. If stored or transported at a different temperature, the ink should be allowed to reach room temperature before calibration or printing. This may have on adverse effect on performance and will affect any warranties given by AFFORD Industrial.

Recommended shelf life of this product is 24 months from the date of manufacture when stored under preferred conditions.

Environmental Information:

98 Series inks are formulated to be free from aromatic hydrocarbons and any volatile components and can therefore be considered to have a lower impact on the environment, when compared with solvent based products, the inks do not contain any ozone depleting chemicals as described in the Montreal Convention.





Dehesa Mari Martí 28600 Navalcarnero (Madrid) Spain Tel +34 916 421 789 - Fax +34 916 421 834 general@afford-inks.com - www.afford-inks.com

Colour Range Table:

\mathcal{I}	000 - TRANS- PARENT BASE	V	001 - VARNISH GLOSS	002 - PROCESS YELLOW	005 - PROCESS MAGENTA EXTRA	006 - PROCESS BLUE	009 - PROCESS BLACK	024 - PROCESS YELLOW EXTRA	052 - PROCESS MAGENTA
	110- EXTRA WHITE OPAQUE		111 - SILVER	115 - HIGH RESISTENCE SILVER	222 - GOLD	229 - LEMON YELLOW	239 - PRIMROSE YELLOW	309 - ORANJE	420 - INTENSE RED
	500 - MAGENTA EXTRA		600 - PERMA- NENT BLUE	604 - REDDISH BLUE	700 - VIOLET	800 - PERMA- NENT GREEN	888 - HIGH PERFORANCE LUMINESCENT	900 - BLACK	

Afford Quality Statement:

Afford Industrial SL assures the quality of this product. Afford cannot, however, guarantee the finished results because Afford exercises no control over individual operating and production procedures. While technical information and advice on the use of this product is provided in good faith, the user bears sole responsibility for selecting the appropriate product for their end use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life cycle from proofing, printing, post print processing, and shipment to end use. This product has been specially formulated for use with the printing process indicated within the technical information, and it has not been tested by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Afford Industrial SL.

Support:

Afford Industrial are a company with international sales coverage, and as such can offer technical, engineering and sales support to our customers worldwide. If you require more information regarding this product, or any of our extensive range of products for screen, pad, digital, flexo and gravure print processes, please contact your local sales representative.

Disclaimer:

All information on this data sheet is based on laboratory tests carried out by Afford Industrial S.L. and from end user experience in print shops. Procedures and directions for use of Afford Industrial products (including printing and after-treatment) must be considered as recommendations only, with no warranties expressed or implied. The user of the products described herein is solely responsible for determining suitability of any Afford Industrial product(s) for the chosen application. Afford Industrial recommends that all products be pre-tested prior to full-scale production use. Also, the user must make sure he complies with the current legislation situation of patents and third party rights when applicable. This data sheet supersedes all previous publications. January 2021.



02/2021